

## ALUMINIUM EXTRUSION ROD, BAR, SHAPES, TUBE, WIRE

### TYPICAL APPLICATIONS

Aerospace Components  
Defence Components  
High Technology Applications

### PRODUCT DESCRIPTION

A high strength 5.1 to 6.1% Zinc alloy. Solution treated, artificially aged and controlled stretched to achieve the T6511 condition, in extruded bar and profile form.  
General Engineering Euronorm - EN 573 / 755  
AECMA Euronorm - BS Pr EN 2394, 2631

### STOCK RANGE

**Round Bar** : 9/16" to 9" Diameter  
(14.28 to 228.6mm)  
**Flat & Squares** : 1 1/2" Square to 8" X 6"  
(38.1mm Square to  
203.2 X 152.4mm)

### CUT TO SIZE SAWN BLANKS

Cut to Length + 1.0mm - NIL

### MACHINABILITY

Very Good

### CORROSION RESISTANCE

Resistance to Atmospheric Attack  
Fair

### SURFACE TREATMENT

#### Anodising

Protective - Fair  
Bright - Variable  
Hard - Fair  
Colour - Fair

#### Plating

N/A

#### Vitreous Enamelling

N/A

### WELDABILITY

Brazing & Soldering - Not Recommended  
Oxygen - Not Recommended  
Inert Gas - Not Recommended  
Resistance, Spot, Beam - Very Good

### PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Tables 11.2 to 11.14 of U.S. Aluminium Standards & Data. For further assistance please contact our Sales Dept / Laboratory.

### CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min	REM			1.20		2.10	0.18	5.10		0.05 Each (Max)
Max	REM	0.40	0.50	2.00	0.30	2.90	0.28	6.10	0.20	0.15 Total

### MECHANICAL PROPERTIES (MINIMA)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65 √ S <sub>0</sub> (%)	Elongation on 50mm (%)
Up to 0.249	78	70	-	7
0.250 - 0.499	81	73	-	7
0.500 - 1.499	81	72	-	7
1.500 - 2.999	81	72	-	7
3.000 - 4.499 Up to 20 sq. in	81	71	-	7
3.000 - 4.499 20 - 32 sq. in	78	70	-	6
4.500 - 5.000	78	68	-	6

### TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

### Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom  
Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com  
All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007