

ALUMINIUM EXTRUSION, ROD, BAR, SHAPES, TUBE, WIRE

TYPICAL APPLICATIONS

Aerospace Components
Defence Components
High Technology Applications

PRODUCT DESCRIPTION

A high strength 3.8 to 4.9% Copper alloy in extruded bar and profile form. Solution heat-treated and controlled stretched to achieve the T3511 condition, produced to the American Standard.

General Engineering Euronorm - EN 573 / 755
AECMA Euronorm - BS EN 2318, 2633
BS Pr EN 2321, 2638

STOCK RANGE

Round Bar : 1/2" to 9" Diameter
(12.7 to 228.6mm)

Flat & Squares : 1 1/4" Square to 8" X 4"
(31.75mm Square to
203.2 X 101.6mm)

CUT TO SIZE SAWN BLANKS

Cut to Length + 1.0mm - NIL

MACHINABILITY

Very Good

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Poor

SURFACE TREATMENT

Anodising

Protective - Fair
Bright - Variable
Hard - Good
Colour - Fair (Dark Colours Only)

Plating

Very Good

Vitreous Enamelling

Unsuitable

WELDABILITY

Brazing & Soldering - Not Recommended
Oxygen - Not Recommended
Inert Gas - Not Recommended
Resistance, Spot, Beam - Excellent

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Tables 11.2 to 11.14 of U.S. Aluminium Standards & Data. For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min	REM			3.8	0.3	1.2				0.05 Each Max
Max	REM	0.5	0.5	4.9	0.9	1.8	0.1	0.25	0.15	0.15 Total

MECHANICAL PROPERTIES (MINIMA)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65 √ S ₀ (%)	Elongation on 50mm (%)
Up to 0.249	57	42	-	12
0.250 - 0.749	60	44	-	12
0.750 - 1.499	65	46	-	10
1.500 and over Up to 25 sq. in	70	52	-	10
1.500 and over Up to 32 sq. in	68	48	-	8

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007