

LOW ALLOY NITRIDING STEEL

TYPICAL APPLICATIONS

High strength mechanical engineering parts in Aeronautical Construction, Autosport and General Mechanical Engineering.

PRODUCT DESCRIPTION

32 CDV 13 in the French AIR 9160 aeronautical specifications is a 3% Cr-Mo-V nitriding steel offering a tensile strength of up to over 1,300 MPa and which develops a hard (around 850 HV), wear resistant surface after nitriding treatment. The alloy is usually produced by single electric melting and vacuum degassing but is also available as a vacuum arc remelted (VAR) version designated with the prefix (E). Material is ultrasonically tested.

The alloy can be employed for high strength non-nitrided parts or for nitrided components where high mechanical properties are required in the core.

Bars are usually supplied in the annealed condition. Final heat treatment consists of hardening at 950°C (oil quench) followed by tempering at a temperature appropriate to the balance of strength and ductility required (refer to published standard and table below).

MATERIAL SPECIFICATIONS

- AIR 9160 - 32 CDV 13 (single melted)
- AIR 9160 - (E) 32 CDV 13 (VAR)
- AMS 6481 (related specification)

AVAILABILITY

Round bar

CHEMICAL COMPOSITION (WEIGHT %)

	C	Si	Mn	P	S	Cr	Mo	Ni	V	Fe
Min	0.29	0.10	0.40			2.80	0.70		0.15	Rem.
Max	0.36	0.40	0.70	0.025	0.020	3.30	1.20	0.30	0.35	Rem.

MECHANICAL PROPERTIES (FOR Q+T NITRIDED PARTS ≤ 80MM DIAM.)

	UTS, MPa	Elongation min., % on 5.65√S(A)	ISO Impact Value min., J	Nitrided layer hardness min., HV5
Tempered ≥ 640°C	950/1100	14	12	700
Tempered ≥ 620°C	1080/1280	12	10	700

The maximum hardness in the annealed condition is 248 HB.

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007