

CHROMIUM MOLYBDENUM ALLOY STEEL BAR

TYPICAL APPLICATIONS

Intended for general use for parts with sections ½” or less in thickness at time of heat treatment which require a through-hardening steel capable of developing hardness as high as Rockwell “C” 50; also for fittings and forgings of greater hardness or variation in thickness at proportionately lower hardnesses. It is frequently used in applications in which 8640 (MIL-S-6049) is specified.

PRODUCT DESCRIPTION

This chromium-molybdenum alloy is a deep hardening steel used where strength and impact toughness are required. It has high fatigue strength making it suitable for critical stressed applications at normal as well as elevated temperatures. For increased resistance to wear and abrasion, it may be nitrided.

This grade is a quality product melted under the best of steelmaking practices for aircraft quality steels. It is vacuum degassed to meet the magnetic particle inspection standards of AMS 2301.

Supplied in the normalised and cold finished, hot finished and normalised or normalised and cold finished condition. The density of this material is typically 7.85kg/dm³.

RELATED SPECIFICATIONS

SAE 4140
UNS G41400

CHEMICAL COMPOSITION (WEIGHT %)

	C	Mn	Si	P	S	Cr	Mo
Min	0.38	0.75	0.20			0.80	0.15
Max	0.43	1.00	0.35	0.025	0.025	1.10	0.25

MECHANICAL PROPERTIES

Ultimate Tensile Strength : 861.8 MPa (Max)

Hardness relates to normalised and cold finished bars 12.70mm and under. Bars over 12.70mm hot finished and normalised or normalised and cold finished hardness 229HB. Product ordered normalised and cold finished shall have hardness not higher than 241 HB.

Hardenability: Shall be J6/16inch (9.5mm) = 50HRC min. and J9/16inch (14mm)= 44HRC min. determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalised at 1700 degsF+/-10 (927 degsC+/-6) and the test specimen austenised at 1550 degsF+/-10 (843degsC+/-6).

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

STOCK RANGE

Round Bar : ¼” to 12” Diameter
(6.35 to 304.8mm)
(Various conditions)

Various in square, flat & hexagon.

CUT TO SIZE SAWN BLANKS

Cut to Length + 1.0mm - NIL

MACHINABILITY

65% based on AISI 1212 is 100% machinability.

CORROSION RESISTANCE

Low resistance to corrosion.

WELDABILITY

Fair.

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Table AMS 2251. For further assistance please contact our Sales Dept / Laboratory.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007