

## HIGH CONDUCTIVITY COPPER BERYLLIUM ALLOY

### TYPICAL APPLICATIONS

Thermal management, Metal and plastic moulding, Welding, Automotive, Marine, Chemical processing

### PRODUCT DESCRIPTION

Alloy 3 is a high conductivity copper beryllium alloy used in applications requiring a combination of high thermal conductivity with moderate strength. Alloy 3, supplied with certified mechanical properties, is fully heat treated and no additional treatment is required. Alloy 3 is nonmagnetic and provides excellent resistance to thermal fatigue.

### CORROSION RESISTANCE

Alloy 3's corrosion resistance is similar to pure copper. It resists corrosion in sea water, most organic solutions, non-oxidizing acids, and dilute alkalis. Alloy 3 is not subject to hydrogen embrittlement, and it resists stress corrosion cracking in sulfide and chloride solutions. Alloy 3 is not recommended for use with ammonium hydroxide or strongly oxidizing acids.

### HIGH TEMPERATURE STRENGTH

Temperature, °C	200	300	400	450	500
UTS, MPa	760	760	730	680	520

### MATERIAL SPECIFICATIONS

- UNS C17510
- ASTM B441
- RWMA – Class 3
- BS EN 12163:1998

### FABRICATION

Machining – very good  
 Brazing – good  
 Electro-discharge machining – good  
 Welding – fair

### AVAILABILITY

Bar, rod, plate, wire, tube, extrusions, forgings

### CHEMICAL COMPOSITION

Alloy 3 in weight %

Be	Ni	Fe	Cu
0.2-0.6	1.4-2.2	.1 max	balance

### MECHANICAL PROPERTIES

	Alloy 3 AT	Alloy 3 HT
UTS, MPa	680-900	750-970
0.2% PS, MPa	550-690	650-870
Elongation, % in 4D	10-25	5-25
Hardness, HRB	92-100	95-102
Fatigue strength at 10 <sup>8</sup> , MPa	240-350	240-350
Elastic modulus, GPa	138	138
Thermal conductivity, W/m °C	240	240
Electrical conductivity, MS/m	32	32
Thermal expansion, ppm/°C	18	18
Magnetic permeability	1.000	1.000
Density, g/cm <sup>3</sup>	8.83	8.83

### Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007