

MARAGING STEEL

TYPICAL APPLICATIONS

Missile casings
Tooling
Ordnance mounting blocks
High performance autosport components
Couplings
Jet engine and helicopter drive shafts
Load cells

MATERIAL SPECIFICATIONS

- UNS K92890
- AMS 6512
- Wr. N 1.6359
- BS S162

AVAILABILITY

Bar and forgings.

PRODUCT DESCRIPTION

Type C250 cobalt containing grade of maraging steel, produced by vacuum arc remelting, provides very high strength (nominally 250 ksi tensile) with an above average level of toughness.

The alloy retains its strength up to 450°C and good notch impact is maintained down to minus 50°C and below. This material may be nitrided.

C250 is usually supplied in the annealed condition where the microstructure consists of fine martensite. This structure is then maraged (precipitation hardened) to achieve final properties employing a relatively low temperature that results in the required combination of high strength and toughness.

The alloy has a density of 8.02 g/cc.

MACHINING AND WELDING

Maraging steels are usually machined in the annealed condition, however, they can be machined in the maraged condition. Components can be machined close to finished dimensions as the low temperature maraging treatment results in minimal distortion. In addition, the small contraction of approximately 0.05% due to maraging results in good dimensional stability.

C250 steel can be readily welded.

CORROSION RESISTANCE

The corrosion resistance of C250 maraging steel is similar to that of standard martensitic stainless steels.

CHEMICAL COMPOSITION

Weight%	C	Si	Mn	Ni	Co	Mo	Al	Ti	Fe
Min.				17.00	7.00	4.60	0.05	0.30	Bal.
Max.	0.3	0.10	0.10	19.00	8.50	5.20	0.15	0.50	

TYPICAL MECHANICAL PROPERTIES (annealed and maraged condition)

UTS, MPa	1,860
0.2% PS, MPa	1,725
Elongation on 4D, %	12
Charpy notch impact, J	20
Young's modulus, GPa	190

Hardness (HRC) in the annealed condition is 34 max. and for the maraged condition 48 min.

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007