

TITANIUM

TYPICAL APPLICATIONS

Components/equipment for architecture, medical engineering, automotive, chemical plant, pharmaceutical, brewing, food, oil & gas, pulp & paper and marine industries.

PRODUCT DESCRIPTION

CP (Commercially Pure) Grade 2 is the most frequently employed unalloyed titanium grade. It provides moderate strength (typical yield strength 352 MPa) combined with good ductility and formability and excellent weldability. Grade 2 titanium has a density of 4.51 g/cc - less than 60% that of steel.

CORROSION RESISTANCE

This material offers high corrosion resistance in oxidising, neutral and mildly reducing media, including chlorides.

MATERIAL SPECIFICATIONS

- UNS R50400
- ASTM B348 Grade 2
- BS TA 2 to 5
- AMS 4902
- AIR 9182 T-40
- ASTM 265 Grade 2

FABRICATION

Weldability – excellent
 Specified bend radius for <0.070 in. x thickness – 2.0
 Specified bend radius for >0.070 in. x thickness – 2.5
 Welded bend radius x thickness – 3.0 (min.)

AVAILABILITY

Bar, wire, strip, sheet, plate, foil, extrusions, forgings, seamless and welded pipe/tube.

CHEMICAL COMPOSITION

Weight %	C	Fe	N ₂	O ₂	H ₂ (sheet)	H(bar)	Ti
Min.							
Max.	0.1	0.3	0.03	0.25	0.015	0.0125	Balance

MECHANICAL PROPERTIES

	Minimum	Typical
UTS, MPa	345	483
0.2% PS, MPa	276	352
Elongation on 2 in., %	20	28
Reduction of area, %	35	-
Elastic modulus, GPa	-	103
Charpy, V notch impact, J	41	-
Hardness, HBN	-	160

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007