

ALUMINIUM EXTRUSION BAR, TUBE, SPECIAL SHAPE

TYPICAL APPLICATIONS

Aerospace & Defence Components
High Technology Applications

PRODUCT DESCRIPTION

A high strength 5.1 to 6.1% Zinc alloy, produced in extruded bar and profile form. Solution treated and artificially over-aged to achieve best stress corrosion resistance and controlled stretched (T73511 condition).

General Engineering Euronorm - EN 573 / 755

AECMA Euronorm - BS EN 2127, 2632

BS Pr EN 2315

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Fair

SURFACE TREATMENT

Anodising

Protective - Fair
Bright - Variable
Hard - Fair
Colour - Fair

Plating

N/A

Vitreous Enamelling

N/A

STOCK RANGE

Round Bar : 1/2" to 8" Diameter
(12.7 to 203.2mm)

Flat & Squares : Various

CUT TO SIZE SAWN BLANKS

Cut to Length + 1.0mm - NIL

MACHINABILITY

Very Good

WELDABILITY

Brazing & Soldering - Not Recommended
Oxygen - Not Recommended
Inert Gas - Not Recommended
Resistance, Spot, Beam - Very Good

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Section 5 of BS 4L100 – Tables 5 (C1, 2, 3, 4, 5, 6, 7 & 8). For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti + Zr	Ti	Others
Min	REM			1.2		2.1	0.18	5.1			
Max	REM	0.40	0.50	2.0	0.30	2.9	0.28	6.1	0.25	0.20	0.05

MECHANICAL PROPERTIES (MINIMA)

Size Range (mm)		Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on $5.65 \sqrt{S_0}$ (%)	Elongation on 50mm (%)
Over	Up to & Including				
-	10	470	400	8	7
10	20	485	420	8	-
20	50	485	415	8	-
50	75	475	410	8	-
75	100	450	380	7	-
100	150	425	365	7	-

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007