

TITANIUM ALLOY

TYPICAL APPLICATIONS

Jet engine compressors
Airframe structures
High performance racing engine components

MATERIAL SPECIFICATIONS

- ASTM UNS R54620
- AMS 4975, 4976 and 4919
- MIL T – 9046 and -9047G

PRODUCT DESCRIPTION

6-2-4-2 is a weldable, near-alpha titanium alloy offering excellent mechanical strength, stability and creep resistance to temperatures as high as 550°C.

Corrosion resistance is good.

The weldability of 6-2-4-2 alloy is fair.

Density is 4.54 g/cc.

AVAILABILITY

Round bar
Sheet
Plate

CHEMICAL COMPOSITION (WEIGHT %)

	C	N	O	Fe	Al	Sn	Zn	Mo	Si	H
Min.					5.5	1.75	3.5	1.75		
Max.	0.08	0.05	0.12	0.25	6.5	2.25	4.5	2.25	0.10	0.0125

MECHANICAL PROPERTIES (MINIMA AT RT FOR DUPLEX ANNEALED BAR)

UTS, MPa	0.2% PS, MPa	Elongation, % in 51mm GL	Reduction in area, %
896	827	10	25

The nominal hardness is 34 HRC.

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom

Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2008