

## SUPER DUPLEX STAINLESS STEEL

### TYPICAL APPLICATIONS

Pumps, valves, chokes, Xmas trees, pipework / flanges, bolting, connectors & manifolds. In oil and gas industry. Equipment in defence, chemical and marine industries.

### PRODUCT DESCRIPTION

Material to UNS S32760 (and the other specifications listed below) is described as a super duplex stainless steel with a microstructure of 50:50 austenite and ferrite. The steel combines high mechanical strength (typically up to 600 MPa yield strength) and good ductility with outstanding corrosion resistance to marine environments and a wide, diverse range of oil & gas production environments. The alloy is supplied with a PREn (Pitting Resistance Equivalent) at >40.0 which guarantees high resistance to pitting corrosion. In addition, the steel offers high resistance to crevice corrosion and stress corrosion cracking. Ambient and subzero (down to minus 50°C) notch ductility is good. These attributes mean that this super duplex steel can be used successfully as an alternative to 300 series stainless steel (such as type 316), standard 22%

Cr duplex steel and precipitation hardening stainless steels. Where appropriate the alloy can be considered in lieu of more costly Grade 5 titanium or nickel based alloys.

### AVAILABILITY

Bar, forgings, sheet, plate, pipe, tube, closed die forgings, flanges and welding consumables.

### MATERIAL SPECIFICATIONS

- UNS S32760 in various ASTM product form specifications
- EN 10088-3 1.4501 (Grade X2CrNiMoCuWN25-7-4)
- NORSOK MDS D51 to D55, D57 & D58
- ASTM A182 F55
- NACE MR01-75 (latest revision) / ISO 15156

### MACHINABILITY / WELDING

The machining and welding of this grade of super duplex stainless steel presents no particular problems. Guidance notes are available upon request.

### CHEMICAL COMPOSITION %

Weight (%)	C	Mn	Si	S	P	Cr	Ni	Mo	Cu	N	W	PREn
Min.						24.0	6.0	3.0	0.50	0.20	0.50	40.0
Max	0.03	1.00	1.00	0.015	0.035	26.0	8.0	4.0	1.00	0.30	1.00	

PREn = Cr % + 3.3Mo% + 16N%

### MINIMUM MECHANICAL PROPERTIES AT ROOM TEMPERATURE (EN 10088-3 1.4501 MAX DIAMETER 160mm – SOLUTION TREATED)

Ultimate Tensile Strength	730 – 930 MPa	( 106 – 135 ksi )
0.2% Proof Strength	530 MPa	( 77 ksi )
Elongation	25 %	
Hardness (Max)	290 HB	
Impact	100 J	( 74 ft.lb )

### TYPICAL PHYSICAL PROPERTIES

Density	7.8	kg/dm <sup>3</sup>
Specific Thermal Capacity at 20°C	500	J.Kg <sup>-1</sup> .K <sup>-1</sup>
Mean Coefficient of Thermal Expansion at 20 - 100°C	13.0	x 10 <sup>-6</sup> K <sup>-1</sup>
Thermal Conductivity at 20°C	15	W.m <sup>-1</sup> .K <sup>-1</sup>
Electrical Resistivity at 20°C	0.80	Ω .mm <sup>2</sup> .m <sup>-1</sup>
Modulus of Elasticity at 20°C	200	GPa
Magnetisable	Yes	

### TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

### Advanced Metals International

Unit O, Stratton Business Park, London Road, Biggleswade, Bedfordshire SG18 8QB United Kingdom  
 Tel: +44 (0) 1767 604 710 Fax: +44 (0) 01767 315 340 Email: sales@advancedmetals.com Website: www.advancedmetals.com  
 All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Advanced Metals International 2007