

5052 Aluminium Tube

Smiths Advanced Metals



Rev: SAM/datasheets/aluminium/5052-tube/feb-2022

Page: 1 of 1

Medium Strength Aluminium Tube

Greater strength than 5251 & 3003 alloys

5052 aluminium tube is a medium strength product with medium to high fatigue strength. The alloy offers slightly better strength than 5251.

The product is a non-heat-treatable aluminium alloy but may be hardened by cold working. Our tubes are easily formed and welded, and the alloy finds use in various aerospace and offshore industries. Our 5052 aluminium tubes offer slightly improved corrosion resistance when compared to 1200 alloys. Our material is not susceptible to stress corrosion cracking (SSC), unlike other aluminium alloys with a manganese content greater than 3.5%.

We have available [5052 aluminium tubes](#) in a wide range of sizes and TO temper.



Grades / Specifications

- AMS4071
- AMS-WW-T-700/4
- ASTM B210
- BS EN 573, BS EN 755, BS EN 754

Key Applications

- Aerospace components
- Marine components
- Heat exchangers

Chemical Composition (weight %)

	Si	Fe	Cu	Mn	Mg	Cr	Zn	Others (ea)	Others (total)	Al
min.					2.20	0.15				Rem
max.	0.25	0.40	0.10	0.10	2.80	0.35	0.10	0.05	0.15	

The Marine Sector


5052 aluminium tubes are commonly used throughout the marine sector in structures, fuel lines, heat exchangers and tanks.

The alloy is a good choice for chlorine, wastewater and saltwater environments and is regarded as one of the best welding aluminiums.

From above-sea to sub-sea applications, 5052 tubing offers an engineering material alternative which promotes a good strength to weight ratio.

Call Smiths Advanced Metals today on

+44 (0)1767 604710



Benefits

- Excellent corrosion resistance
- Good formability
- Good weldability

www.smithsadvanced.com
info@smithsadvanced.com


Unit 5 Percy Road,
Huntingdon,
Cambridgeshire PE29 6SZ
Tel: **+44 (0) 1767 604710**



ISO 9001
Quality
Management
Systems
CERTIFIED

AS/EN
9100
Aviation Space and
Defence
CERTIFIED

EN 9120
Aviation Space and
Defence
CERTIFIED



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.

© Smiths Advanced Metals 2025